

AKROMID®

T5 GF 30 8 black (6457)

PPA GF30

AKROMID® T5 GF 30 8 black (6457) is a 30% glass fibre reinforced polyphthalamide with high rigidity and strength, as well as high temperature and chemical resistance. This aromatic PPA keeps mechanical performance even at elevated temperatures as well as moisture pick-up. The material fulfills the requirements according to ACS and NSF 61. It is suitable for applications that are in contact with cold and hot drinking water. This material corresponds to the European food guideline EU 10/2011 and to the American FDA 21 CFR and is suitable for parts of kitchen and household appliances.

Regulatory



Properties

Modulus

11.500 MPa

Strength

210 MPa

Impact

65 kJ/m²

Mechanical Properties

Tensile modulus

ISO 527-2

1 mm/min | d.a.m.

11500 MPa

Tensile stress at break

ISO 527-2

5 mm/min | d.a.m.

210 MPa

Tensile strain at break

ISO 527-2

5 mm/min | d.a.m.

2,3 %

Flexural modulus

ISO 178

2 mm/min | d.a.m.

11000 MPa

Flexural strength

ISO 178

2 mm/min | d.a.m.

310 MPa

Charpy impact strength

ISO 179-1/1eU

23°C | d.a.m.

65 kJ/m²

Charpy notched impact strength

ISO 179-1/1eA

23°C | d.a.m.

8,5 kJ/m²

Thermal Properties

| | | |
|---|--------------|---------------|
| Temperature of deflection under load HDT/A ISO 75 | 1,8 MPa | 270 °C |
| Temperature of deflection under load HDT/C ISO 75 | 8 MPa | 155 °C |
| Melting temperature ISO 11357-3 | DSC, 10K/min | 325 °C |

General Properties

| | | |
|---------------------------------------|------------|------------------------------|
| Density ISO 1183 | 23°C | 1,43 g/cm³ |
| Molding shrinkage ISO 294-4 | flow | 0,2 - 0,4 % |
| | transverse | 0,6 - 0,8 % |

Processing

The values mentioned are recommendations. We only recommend desiccant / dry air dryers or vacuum dryers. Too long a drying time and the resulting residual moisture content below the lower limit can lead to filling problems and surface defects. The specified drying time refers to closed and undamaged bagged material. When processing from previously opened bags or from octabins with polyolefin inliners, a longer drying time may be necessary. It is recommended to check the residual moisture content after the drying process.



| | | |
|----------|--|----------------|
| D | Drying time | 0 - 4 h |
| | Drying temperature ($\tau \leq -30^{\circ}\text{C}$) | 120 °C |
| | Processing moisture | 0,02 - 0,1 % |
| 1 | Feed section | 60 - 90 °C |
| 2 | Temperature Zone 1 - Zone 4 | 320 - 350 °C |
| 3 | Nozzle temperature | 330 - 350 °C |
| 4 | Melt temperature | 330 - 350 °C |
| 5 | Mold temperature | 120 - 160 °C |
| → | Holding pressure, spec. | 300 - 800 bar |
| ← | Back pressure, spec. | 50 - 150 bar |
| | Injection speed | medium to high |
| | Screw speed | 8 - 15 m/min |

Diagrams

