

Technical Data Sheet



ALCOM PA6 900/1 CF15 IM

MOCOM

Base Polymer	Polyamide 6
Filler/Additive System	15 % carbon fibres
Special Features	electrically conductive, reduced surface resistivity, heat stabilised, impact modified
Market Segment	Automotive, Machinery
Application Area	injection moulded parts
Typical Applications	bearings and sliding elements, functional components

Pre-Drying Conditions 80 °C in a dry air (dessiccant) dryer
for 2-12 h
max. moisture content <0,15 %

Processing Injection Moulding melt temperature 270-290 °C
mould temperature 80-100 °C

Storage dry, protected from light

Properties	dry/cond.	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	8400 / 5100	MPa	ISO 178
Flexural Strength	200 / 125	MPa	ISO 178
Tensile Modulus	10500 / 5900	MPa	ISO 527
Tensile Strength at Break	140 / 90	MPa	ISO 527
Tensile Elongation at Break	3.1 / 6.7	%	ISO 527
Impact Strength (Charpy, 23°C)	60 / 90	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	55 / -	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	16 / 28	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	8 / -	kJ/m ²	ISO 179/1eA
Thermal Properties			
HDT / A (1,8 MPa)	210 / *	°C	ISO 75-1/-2
DSC (Melt Point)	220 / *	°C	ISO 11357
Electrical Properties			
Surface Resistance	* / 750	Ohm	IEC 62631-3-2
Rheological Properties			
Shrinkage (lengthwise, 24h)	0.1 - 0.3	%	ISO 294-4
Shrinkage (lateral, 24h)	0.3 - 0.5	%	ISO 294-4
Physical Properties			
Density	1150 / -	kg/m ³	ISO 1183