

Technical Data Sheet



ALTECH PA6 A 1000/110 IM

MOCOM

Base Polymer	Polyamide 6
Colour	black,natural color,grey,blue,green,white
Special Features	high impact modified,dry impact modified,easy release (demoulding),easy flow
Market Segment	Machinery,Automotive
Application Area	exterior parts,interior decoration / finishing,pump components
Typical Applications	housings,clips,functional components,protection-strip

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-12 h dependant on moisture content max. moisture content <0,15 %
-----------------------	---

Processing Injection Moulding	melt temperature 250-270 °C mould temperature 60-100 °C
-------------------------------	--

Storage	dry, protected from light
---------	---------------------------

Properties	dry/cond.	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2300 / 800	MPa	ISO 178
Flexural Stress (3.5% Strain)	75 / 23	MPa	ISO 178
Tensile Modulus	2600 / 900	MPa	ISO 527
Tensile Stress at Yield	65 / 35	MPa	ISO 527
Tensile Elongation at Yield	3.5 / 25	%	ISO 527
Tensile Elongation at Break	20 / -	%	ISO 527
Impact Strength (Charpy, 23°C)	no break / 1000	kJ/m²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	no break / -	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	12 / 100	kJ/m²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	8.5 / -	kJ/m²	ISO 179/1eA
Thermal Properties			
HDT / A (1,8 MPa)	60 / *	°C	ISO 75-1/-2
DSC (Melt Point)	220 / *	°C	ISO 11357
Rheological Properties			
Shrinkage (lengthwise, 24h)	1.4 - 1.8	%	ISO 294-4
Shrinkage (lateral, 24h)	1.8 - 2.2	%	ISO 294-4
Physical Properties			
Density	1110 / -	kg/m³	ISO 1183
Flammability			
Flammability (1.5 mm)	HB / *	class	UL 94