

Technical Data Sheet



ALTECH PA6 B 1000/270

MOCOM

Base Polymer	Polyamide 6
Colour	black,grey
Special Features	good flow,easy release (demoulding)
Market Segment	building and construction
Application Area	exterior parts,injection moulded parts
Typical Applications	housings,clips,functional components

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-12 h dependant on moisture content 0,15 % max. moisture content
Processing Injection Moulding	melt temperature 250-270 °C mould temperature 60-100 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2700	MPa	ISO 178
Flexural Stress (3.5% Strain)	90	MPa	ISO 178
Tensile Modulus	3000	MPa	ISO 527
Tensile Stress at Yield	85	MPa	ISO 527
Tensile Elongation at Yield	3.8	%	ISO 527
Tensile Elongation at Break	20	%	ISO 527
Impact Strength (Charpy, 23°C)	75	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	no break	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	5	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	5	kJ/m ²	ISO 179/1eA
Thermal Properties			
HDT / A (1,8 MPa)	65	°C	ISO 75-1/-2
DSC (Melt Point)	220	°C	ISO 11357
Rheological Properties			
Shrinkage (lengthwise, 24h)	1.2 - 1.6	%	ISO 294-4
Shrinkage (lateral, 24h)	1.4 - 1.8	%	ISO 294-4
Physical Properties			
Density	1130	kg/m ³	ISO 1183