

Technical Data Sheet



ALTECH PA6 FC 2030/100 GF30

MOCOM

Base Polymer	Polyamide 6
Filler/Additive System	30 % glass fibres
Colour	natural color
Special Features	heat stabilised,easy release (demoulding),processing stabilised
Market Segment	electrical and electronic,building and construction,sport and leisure,food processing industry
Application Area	injection moulded parts,food contact
Typical Applications	housings,kitchenware

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-12 h dependant on moisture content max. moisture content <0,15 %
Processing Injection Moulding	melt temperature 270-290 °C mould temperature 80-100 °C
Storage	dry, protected from light
Minimum Shelf Life	months <12

Properties	dry/cond.	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	8500 / 5300	MPa	ISO 178
Flexural Strength	240 / 155	MPa	ISO 178
Tensile Modulus	9300 / 5800	MPa	ISO 527
Tensile Strength at Break	165 / 105	MPa	ISO 527
Tensile Elongation at Break	3.4 / 6	%	ISO 527
Impact Strength (Charpy, 23°C)	75 / 90	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	60 / -	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	10 / 18	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	7.5 / -	kJ/m ²	ISO 179/1eA
Thermal Properties			
HDT / A (1,8 MPa)	215 / *	°C	ISO 75-1/-2
DSC (Melt Point)	220 / *	°C	ISO 11357
Rheological Properties			
Shrinkage (lengthwise, 24h)	0.2 - 0.4	%	ISO 294-4
Shrinkage (lateral, 24h)	0.6 - 0.8	%	ISO 294-4
Physical Properties			
Density	1360 / -	kg/m ³	ISO 1183