

Technical Data Sheet



ALCOM PA66 910/1.1 CF15 GF20

MOCOM

Base Polymer	Polyamide 66
Filler/Additive System	15 % carbon fibres, 20 % glass fibres
Special Features	electrically conductive, reduced surface resistivity, improved sliding / wear, heat stabilised
Market Segment	Automotive, Machinery
Typical Applications	functional components

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-12 h max. moisture content <0,15 %
Processing Injection Moulding	melt temperature 280-300 °C mould temperature 80-120 °C
Storage	dry, protected from light

Properties	dry/cond.	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	15500 / -	MPa	ISO 178
Flexural Strength	315 / -	MPa	ISO 178
Tensile Modulus	17500 / -	MPa	ISO 527
Tensile Strength at Break	220 / -	MPa	ISO 527
Tensile Elongation at Break	2.2 / -	%	ISO 527
Impact Strength (Charpy, 23°C)	65 / -	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	9 / -	kJ/m²	ISO 179/1eA
Thermal Properties			
HDT / A (1,8 MPa)	260 / *	°C	ISO 75-1/-2
DSC (Melt Point)	263 / *	°C	ISO 11357
Electrical Properties			
Surface Resistance	* / 150	Ohm	IEC 62631-3-2
Rheological Properties			
Shrinkage (lengthwise, 24h)	0.1 - 0.3	%	ISO 294-4
Shrinkage (lateral, 24h)	0.2 - 0.4	%	ISO 294-4
Physical Properties			
Density	1360 / -	kg/m³	ISO 1183