

Technical Data Sheet



ALCOM PBT 700/9 BK2034-06MCS

MOCOM

Base Polymer	Polybutylene Terephthalate
Special Features	matt (textured) surface
Market Segment	building and construction, various
Application Area	fixtures / fittings, household goods, various
Typical Applications	kitchenware, fixing elements, various

Pre-Drying Conditions	in a dry air (dessiccant) dryer 100-120 °C for 2-4 h in an air circulating dryer 100-120 °C for 4-8 h dependant on moisture content
-----------------------	---

Processing Injection Moulding	melt temperature 250-270 °C mould temperature 60-100 °C
-------------------------------	--

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2700	MPa	ISO 178
Flexural Stress (3.5% Strain)	80	MPa	ISO 178
Tensile Modulus	2600	MPa	ISO 527
Tensile Stress at Yield	55	MPa	ISO 527
Tensile Elongation at Yield	3.4	%	ISO 527
Tensile Elongation at Break	12	%	ISO 527
Impact Strength (Charpy, 23°C)	67	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	40	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	3.5	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	3	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	178	°C	ISO 306
HDT / A (1,8 MPa)	61	°C	ISO 75-1/-2
DSC (Melt Point)	226	°C	ISO 11357
Rheological Properties			
Melt Index (MVR)	11	cm ³ /10min	ISO 1133
MVR temperature	250	°C	-
MVR load	2.16	kg	-
Shrinkage (lengthwise, 24h)	2 - 2.4	%	ISO 294-4
Shrinkage (lateral, 24h)	2 - 2.4	%	ISO 294-4
Physical Properties			
Density	1320	kg/m ³	ISO 1183