

Technical Data Sheet



ALCOM LDDC PC 1000 UV BK1044-20

MOCOM

Base Polymer	Polycarbonate
Filler/Additive System	special filler
Special Features	good flow, processing stabilised, UV stabilised, injection moulding grade, translucent, light scattering
Market Segment	Automotive, Lighting
Application Area	lighting, light transparent components, Black Panel-Technology
Typical Applications	lamp covers, display elements, operating elements
Approvals	Stellantis Plastic Material Policy

Pre-Drying Conditions	120 °C in a dry air (dessiccant) dryer for 2-4 h 120 °C in an air circulating dryer for 4-12 h max. moisture content <0,02 %
Processing Injection Moulding	melt temperature 270-310 °C mould temperature 80-110 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2450	MPa	ISO 178
Flexural Stress (3.5% Strain)	76	MPa	ISO 178
Tensile Modulus	2400	MPa	ISO 527
Tensile Stress at Yield	66	MPa	ISO 527
Tensile Elongation at Yield	6	%	ISO 527
Tensile Elongation at Break	60	%	ISO 527
Impact Strength (Charpy, 23 °C)	no break	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40 °C)	no break	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23 °C)	10	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40 °C)	10	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	142	°C	ISO 306
HDT / A (1,8 MPa)	124	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	20	cm ³ /10min	ISO 1133
MVR temperature	300	°C	-
MVR load	1.2	kg	-
Shrinkage (24h)	0.6 - 0.9	%	ISO 294-4

Technical Data Sheet



ALCOM LDDC PC 1000 UV BK1044-20

MOCOM

Physical Properties

Density	1190	kg/m ³	ISO 1183
---------	------	-------------------	----------

Optical Properties

Total Transmission T(Y) (d=1,0mm, A, 2°)	25	%	ISO 13468
Total Transmission T(Y) (d=2,0mm, A, 2°)	7.5	%	ISO 13468
Haze T(Y) (d=1,0 mm, A, 2°)	9.5	%	ISO 13468
Haze T(Y) (d=2,0 mm, A, 2°)	16	%	ISO 13468

Diagrams

Stress-Strain

