

Technical Data Sheet



ALCOM PC 730/5 UV WT1231-10LDX

MOCOM

Base Polymer	Polycarbonate
Filler/Additive System	special filler,UV stabilised
Special Features	translucent,light scattering,high light diffusion,extrusion grade
Market Segment	Automotive,Lighting
Application Area	lighting,light transparent components
Typical Applications	lamp covers

Pre-Drying Conditions	120 °C in a dry air (dessiccant) dryer for 2-4 h 120 °C in an air circulating dryer for 4-12 h max. moisture content <0,02 %
Processing Extrusion	melt temperature 240-280 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2500	MPa	ISO 178
Flexural Stress (3.5% Strain)	76	MPa	ISO 178
Tensile Modulus	2400	MPa	ISO 527
Tensile Stress at Yield	66	MPa	ISO 527
Tensile Elongation at Yield	6	%	ISO 527
Tensile Elongation at Break	50	%	ISO 527
Impact Strength (Charpy, 23°C)	no break	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	no break	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	15	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	15	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	143	°C	ISO 306
HDT / A (1,8 MPa)	129	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	4	cm ³ /10min	ISO 1133
MVR temperature	300	°C	-
MVR load	1.2	kg	-
Shrinkage (24h)	0.6 - 0.8	%	ISO 294-4
Physical Properties			
Density	1200	kg/m ³	ISO 1183

Technical Data Sheet



ALCOM PC 730/5 UV WT1231-10LDX

MOCOM

Flammability

Glow Wire (GWFI, 850°C, 1.0mm)	passed	-	DIN EN 60695
Glow Wire (GWFI, 850°C, 2.0mm)	passed	-	DIN EN 60695

Optical Properties

Total Transmission T(Y) (d=1,0mm, A, 2°)	50	%	ISO 13468
Haze T(Y) (d=1,0 mm, A, 2°)	96	%	ISO 13468
Half Power Angle T(Y) (d=1,0mm, A, 2°)	57	°	-