

Technical Data Sheet



ALTECH PC A 1000/121 UV IM

MOCOM

Base Polymer	Polycarbonate
Filler/Additive System	light stabiliser
Colour	grey,white,black,brown,beige
Special Features	UV stabilised,impact modified,easy release (demoulding),processing stabilised,heat stabilised
Market Segment	Automotive
Application Area	interior decoration / finishing,clothing / fasteners
Typical Applications	functional components,housings,bezels

Pre-Drying Conditions	120 °C in a dry air (dessiccant) dryer for 2-3 h in an air circulating dryer 100-120 °C for 4-12 h dependant on moisture content max. moisture content <0,02 %
-----------------------	---

Processing Injection Moulding	melt temperature 270-310 °C mould temperature 80-110 °C
-------------------------------	--

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Tensile Modulus	2300	MPa	ISO 527
Tensile Stress at Yield	59	MPa	ISO 527
Tensile Elongation at Yield	5.5	%	ISO 527
Tensile Elongation at Break	60	%	ISO 527
Impact Strength (Charpy, 23°C)	no break	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	no break	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	50	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	13	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	140	°C	ISO 306
HDT / A (1,8 MPa)	130	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	30	cm ³ /10min	ISO 1133
MVR temperature	300	°C	-
MVR load	1.2	kg	-
Shrinkage (24h)	0.6 - 0.8	%	ISO 294-4
Physical Properties			
Density	1200	kg/m ³	ISO 1183