

Technical Data Sheet



ALTECH PC A 1000/572 UV

MOCOM

Base Polymer	Polycarbonate
Filler/Additive System	light stabiliser
Colour	grey
Special Features	easy release (demoulding), UV stabilised
Market Segment	building and construction, electrical and electronic
Application Area	interior, electrical and electronic (E&E)
Typical Applications	various, functional components, housings, sockets

Pre-Drying Conditions	120 °C in a dry air (dessiccant) dryer for 2-3 h in an air circulating dryer 100-120 °C for 4-12 h dependant on moisture content max. moisture content <0,02 %
Processing Injection Moulding	melt temperature 270-310 °C mould temperature 80-110 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2500	MPa	ISO 178
Flexural Stress (3.5% Strain)	75	MPa	ISO 178
Tensile Modulus	2400	MPa	ISO 527
Tensile Stress at Yield	62	MPa	ISO 527
Tensile Elongation at Yield	6	%	ISO 527
Tensile Elongation at Break	100	%	ISO 527
Impact Strength (Charpy, 23 °C)	no break	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40 °C)	no break	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23 °C)	12	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40 °C)	12	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	144	°C	ISO 306
HDT / A (1,8 MPa)	131	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	13	cm ³ /10min	ISO 1133
MVR temperature	300	°C	-
MVR load	1.2	kg	-
Shrinkage (24h)	0.5 - 0.8	%	ISO 294-4

Technical Data Sheet



ALTECH PC A 1000/572 UV

MOCOM

Physical Properties

Density	1210	kg/m ³	ISO 1183
---------	------	-------------------	----------

Flammability

Flammability (1.5 mm)	HB	class	UL 94
-----------------------	----	-------	-------