

Technical Data Sheet



ALTECH PC ECO 1000/521 IM UV

MOCOM

Base Polymer	Polycarbonate
Special Features	UV stabilised,easy release (demoulding),impact modified
Market Segment	electrical and electronic,Lighting,various
Application Area	exterior,fixtures / fittings,various
Typical Applications	garden equipment,housings,various

Pre-Drying Conditions	120 °C in a dry air (dessiccant) dryer for 2-4 h in an air circulating dryer 100-120 °C for 4-12 h dependant on moisture content max. moisture content <0,02 %
-----------------------	---

Processing Injection Moulding	melt temperature 270-310 °C mould temperature 80-110 °C
-------------------------------	--

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Tensile Modulus	2200	MPa	ISO 527
Tensile Stress at Yield	62	MPa	ISO 527
Tensile Elongation at Yield	5.7	%	ISO 527
Tensile Elongation at Break	96	%	ISO 527
Impact Strength (Charpy, 23°C)	no break	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	75	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	141	°C	ISO 306
Rheological Properties			
Melt Index (MVR)	8	cm ³ /10min	ISO 1133
MVR temperature	300	°C	-
MVR load	1.2	kg	-
Shrinkage (24h)	0.5 - 0.8	%	ISO 294-4
Physical Properties			
Density	1230	kg/m ³	ISO 1183
Ecological Properties			
Global Warming Potential (GWP)	0.5	kg CO ₂ eq./kg	ISO 14040, 14044
Flammability			
Glow Wire (GWFI, 850°C, 2.0mm)	passed	-	DIN EN 60695