

Technical Data Sheet



ALTECH PC+ASA A 1000/502 UV

MOCOM

Base Polymer	Polycarbonate +Acrylonitrile Styrene Acrylate Blend
Special Features	highly UV stabilised,easy release (demoulding),good flow,injection moulding grade
Market Segment	various,Automotive,building and construction
Application Area	various,exterior parts
Typical Applications	various,garden equipment

Pre-Drying Conditions	in a dry air (dessiccant) dryer 90-110 °C for 2-4 h in an air circulating dryer 90-110 °C for 3-6 h dependant on moisture content
-----------------------	---

Processing Injection Moulding	melt temperature 260-300 °C mould temperature 60-100 °C
-------------------------------	--

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2500	MPa	ISO 178
Flexural Stress (3.5% Strain)	78	MPa	ISO 178
Tensile Modulus	2400	MPa	ISO 527
Tensile Stress at Yield	58	MPa	ISO 527
Tensile Elongation at Yield	4.3	%	ISO 527
Tensile Elongation at Break	35	%	ISO 527
Impact Strength (Charpy, 23°C)	no break	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	no break	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	55	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	10	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	114	°C	ISO 306
HDT / A (1,8 MPa)	103	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	27	cm ³ /10min	ISO 1133
MVR temperature	260	°C	-
MVR load	5	kg	-
Shrinkage (24h)	0.4 - 0.7	%	ISO 294-4
Physical Properties			
Density	1150	kg/m ³	ISO 1183