

Technical Data Sheet



ALCOM WP POM 5020 TF 18029

MOCOM

Base Polymer	Polyoxymethylene Copolymer
Filler/Additive System	20 % PTFE/Aramid
Special Features	improved sliding / wear
Market Segment	Automotive, Machinery
Application Area	gear wheels, roller bearings
Typical Applications	functional components, bearings and sliding elements

Pre-Drying Conditions	in a dry air (dessiccant) dryer 100-110 °C for 2-3 h in an air circulating dryer 100-110 °C for 3-5 h dependant on moisture content
-----------------------	---

Processing Injection Moulding	melt temperature 190-230 °C mould temperature 60-120 °C
-------------------------------	--

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2600	MPa	ISO 178
Flexural Stress (3.5% Strain)	64	MPa	ISO 178
Tensile Modulus	2500	MPa	ISO 527
Tensile Strength at Break	42	MPa	ISO 527
Tensile Elongation at Break	8	%	ISO 527
Impact Strength (Charpy, 23 °C)	31	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40 °C)	31	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23 °C)	3	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40 °C)	2.5	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	148	°C	ISO 306
HDT / A (1,8 MPa)	103	°C	ISO 75-1/-2
DSC (Melt Point)	167	°C	ISO 11357
Rheological Properties			
Melt Index (MVR)	3.5	cm ³ /10min	ISO 1133
MVR temperature	190	°C	-
MVR load	2.16	kg	-
Shrinkage (lengthwise, 24h)	2 - 2.4	%	ISO 294-4
Shrinkage (lateral, 24h)	1.4 - 1.8	%	ISO 294-4

Technical Data Sheet



ALCOM WP POM 5020 TF 18029



Physical Properties

Density	1450	kg/m ³	ISO 1183
---------	------	-------------------	----------

Tribologic Properties

Coefficient of Sliding Friction μ ($p_v = 5 \cdot 1 \text{ MPa} \cdot \text{m/s}$)	0.27	-	ASTM G 137
Coefficient of Sliding Friction μ_H ($p_v = 5 \cdot 1 \text{ MPa} \cdot \text{m/s}$)	0.18	-	ASTM G 137
Specific Wear Rate w_s ($p_v = 5 \cdot 1 \text{ MPa} \cdot \text{m/s}$)	0.25	E-6 mm ³ /Nm	ASTM G 137
Linear Wear Rate w ($p_v = 5 \cdot 1 \text{ MPa} \cdot \text{m/s}$)	4.5	$\mu\text{m/h}$	ASTM G 137