

Technical Data Sheet



ALCOM MED PP 2040 BL1182-19

MOCOM

Base Polymer	Polypropylene Homopolymer
Filler/Additive System	40 % glass fibres
Special Features	chemically coupled
Market Segment	Medical / Personal Care
Typical Applications	housings

Pre-Drying Conditions	in a dry air (dessiccant) dryer 80-120 °C for 2-3 h in an air circulating dryer 80-120 °C for 2-4 h
Processing Injection Moulding	melt temperature 200-270 °C mould temperature 20-90 °C
Storage	dry, protected from light
Minimum Shelf Life	months <24

Properties	Value	Dimension	Based on Test Norm
Mechanical Properties			
Flexural Modulus	8500	MPa	ISO 178
Flexural Strength	160	MPa	ISO 178
Tensile Modulus	9500	MPa	ISO 527
Tensile Strength at Break	110	MPa	ISO 527
Tensile Elongation at Break	2.4	%	ISO 527
Impact Strength (Charpy, 23°C)	50	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	45	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	9	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	8.5	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	143	°C	ISO 306
HDT / A (1,8 MPa)	155	°C	ISO 75-1/-2
DSC (Melt Point)	166	°C	ISO 11357
Rheological Properties			
Melt Index (MVR)	4	cm ³ /10min	ISO 1133
MVR temperature	230	°C	-
MVR load	2.16	kg	-
Shrinkage (lengthwise, 24h)	0.1 - 0.3	%	ISO 294-4
Shrinkage (lateral, 24h)	0.4 - 0.6	%	ISO 294-4
Physical Properties			
Density	1230	kg/m ³	ISO 1183