

Technical Data Sheet

Altech NXT PP®



ALTECH NXT PP-H A 2020/450.02 GF20 CP BK1040-20LWT

MOCOM

Base Polymer	Polypropylene Homopolymer
Filler/Additive System	20 % glass fibres
Special Features	chemically coupled,high heat stabilised,laser transparent,high toughness
Market Segment	Automotive
Typical Applications	various

Pre-Drying Conditions	in an air circulating dryer 80-120 °C for 2-4 h in a dry air (dessiccant) dryer 80-120 °C for 2-3 h
-----------------------	--

Processing Injection Moulding	melt temperature 200-250 °C mould temperature 20-70 °C
-------------------------------	---

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	4000	MPa	ISO 178
Flexural Strength	120	MPa	ISO 178
Tensile Modulus	5200	MPa	ISO 527
Tensile Strength at Break	85	MPa	ISO 527
Tensile Elongation at Break	3.3	%	ISO 527
Impact Strength (Charpy, 23°C)	50	kJ/m²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	33	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	8.5	kJ/m²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	7	kJ/m²	ISO 179/1eA
Thermal Properties			
Vicat B50	138	°C	ISO 306
HDT / A (1,8 MPa)	153	°C	ISO 75-1/-2
DSC (Melt Point)	166	°C	ISO 11357
Rheological Properties			
Melt Index (MVR)	7.5	cm³/10min	ISO 1133
MVR temperature	230	°C	-
MVR load	2.16	kg	-
Shrinkage (lengthwise, 24h)	0.3 - 0.5	%	ISO 294-4
Shrinkage (lateral, 24h)	0.6 - 0.8	%	ISO 294-4
Spiral Flow (2 mm wall thickness)	75	cm	-
Physical Properties			
Density	1050	kg/m³	ISO 1183