

Technical Data Sheet



ALTECH PP-B B 4020/506 MR20

MOCOM

Base Polymer	Polypropylene Copolymer
Filler/Additive System	20 % mineral
Colour	grey,white
Special Features	easy release (demoulding),processing stabilised,heat stabilised,easy flow
Market Segment	packaging,building and construction
Application Area	interior,hygiene products,exterior parts
Typical Applications	housings,functional components,fixing elements

Pre-Drying Conditions	in a dry air (dessiccant) dryer 80-120 °C for 2-3 h in an air circulating dryer 80-120 °C for 2-4 h dependant on moisture content max. moisture content <0,10 %
-----------------------	--

Processing Injection Moulding	melt temperature 200-250 °C mould temperature 20-70 °C
-------------------------------	---

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	1300	MPa	ISO 178
Flexural Stress (3.5% Strain)	31	MPa	ISO 178
Tensile Modulus	1300	MPa	ISO 527
Tensile Stress at Yield	20	MPa	ISO 527
Tensile Elongation at Yield	5	%	ISO 527
Tensile Elongation at Break	130	%	ISO 527
Impact Strength (Charpy, 23°C)	no break	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	40	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	6	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	2	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	70	°C	ISO 306
HDT / A (1,8 MPa)	55	°C	ISO 75-1/-2
DSC (Melt Point)	163	°C	ISO 11357
Rheological Properties			
Melt Index (MVR)	15	cm ³ /10min	ISO 1133
MVR temperature	230	°C	-
MVR load	2.16	kg	-
Shrinkage (lengthwise, 24h)	1.3 - 1.7	%	ISO 294-4
Shrinkage (lateral, 24h)	1 - 1.4	%	ISO 294-4

Technical Data Sheet



ALTECH PP-B B 4020/506 MR20

MOCOM

Physical Properties

Density	1080	kg/m ³	ISO 1183
---------	------	-------------------	----------

Flammability

Flammability (1.5 mm)	HB	class	UL 94
-----------------------	----	-------	-------