

Technical Data Sheet

Altech[®] ECO

ALBIS

ALTECH PP-B ECO 2025/156 CP GF25

MOCOM

Base Polymer	Polypropylene Copolymer
Filler/Additive System	25 % glass fibres
Special Features	high stiffness,processing stabilised,contains recycled material
Market Segment	Machinery,electrical and electronic,building and construction
Typical Applications	housings,handles,containers

Pre-Drying Conditions	in a dry air (dessiccant) dryer 80-120 °C for 2-3 h in an air circulating dryer 80-120 °C for 2-4 h
Processing Injection Moulding	melt temperature 200-250 °C mould temperature 20-70 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	4200	MPa	ISO 178
Flexural Strength	95	MPa	ISO 178
Tensile Modulus	4800	MPa	ISO 527
Tensile Strength at Break	60	MPa	ISO 527
Tensile Elongation at Break	3.3	%	ISO 527
Notched Impact Strength (Izod, 23°C)	8	kJ/m ²	ISO 180/1A
Impact Strength (Charpy, 23°C)	32	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	26	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	7	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	3.5	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	109	°C	ISO 306
HDT / A (1,8 MPa)	131	°C	ISO 75-1/-2
DSC (Melt Point)	163	°C	ISO 11357
Rheological Properties			
Melt Index (MVR)	7	cm ³ /10min	ISO 1133
MVR temperature	230	°C	-
MVR load	2.16	kg	-
Shrinkage (lengthwise, 24h)	0.5 - 0.7	%	ISO 294-4
Shrinkage (lateral, 24h)	0.5 - 0.7	%	ISO 294-4
Physical Properties			
Density	1130	kg/m ³	ISO 1183