

Technical Data Sheet



ALTECH PP-B A 2040/150 GF40 CP

MOCOM

Base Polymer	Polypropylene Heterophasic Copolymer
Filler/Additive System	40 % glass fibres
Colour	black,natural color
Special Features	chemically coupled,easy release (demoulding),heat stabilised
Market Segment	Machinery,electrical and electronic,building and construction
Application Area	sports equipment,interior decoration / finishing,exterior parts,electrical components
Typical Applications	functional components,housings,fixing elements

Pre-Drying Conditions	in a dry air (dessiccant) dryer 80-120 °C for 2-3 h in an air circulating dryer 80-120 °C for 2-4 h dependant on moisture content max. moisture content <0,10 %
-----------------------	--

Processing Injection Moulding	melt temperature 200-250 °C mould temperature 20-70 °C
-------------------------------	---

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	7100	MPa	ISO 178
Flexural Strength	115	MPa	ISO 178
Tensile Modulus	7800	MPa	ISO 527
Tensile Strength	70	MPa	ISO 527
Tensile Elongation at Break	4	%	ISO 527
Impact Strength (Charpy, 23°C)	65	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	16	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	115	°C	ISO 306
HDT / A (1,8 MPa)	145	°C	ISO 75-1/-2
DSC (Melt Point)	166	°C	ISO 11357
Rheological Properties			
Melt Index (MVR)	5	cm ³ /10min	ISO 1133
MVR temperature	230	°C	-
MVR load	2.16	kg	-
Shrinkage (lengthwise, 24h)	0.1 - 0.3	%	ISO 294-4
Shrinkage (lateral, 24h)	0.3 - 0.5	%	ISO 294-4
Physical Properties			
Density	1210	kg/m ³	ISO 1183