

Technical Data Sheet



ALTECH PP-H A 4925/500 MR25

MOCOM

Base Polymer	Polypropylene Homopolymer
Filler/Additive System	25 % talcum
Colour	white
Special Features	heat stabilised,easy release (demoulding),processing stabilised
Market Segment	Furniture,building and construction,Automotive
Application Area	injection moulded parts,interior decoration / finishing
Typical Applications	functional components,housings,fixing elements

Pre-Drying Conditions	in a dry air (dessiccant) dryer 80-120 °C for 2-3 h in an air circulating dryer 80-120 °C for 2-4 h dependant on moisture content max. moisture content <0,10 %
-----------------------	--

Processing Injection Moulding	melt temperature 200-250 °C mould temperature 20-70 °C
-------------------------------	---

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	3000	MPa	ISO 178
Flexural Stress (3.5% Strain)	45	MPa	ISO 178
Tensile Modulus	3000	MPa	ISO 527
Tensile Stress at Yield	32	MPa	ISO 527
Tensile Elongation at Yield	4.6	%	ISO 527
Tensile Elongation at Break	12	%	ISO 527
Impact Strength (Charpy, 23°C)	40	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	3	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	98	°C	ISO 306
HDT / A (1,8 MPa)	80	°C	ISO 75-1/-2
DSC (Melt Point)	163	°C	ISO 11357
Rheological Properties			
Melt Index (MVR)	25	cm ³ /10min	ISO 1133
MVR temperature	230	°C	-
MVR load	2.16	kg	-
Shrinkage (lengthwise, 24h)	0.6 - 0.8	%	ISO 294-4
Shrinkage (lateral, 24h)	1.1 - 1.3	%	ISO 294-4
Physical Properties			
Density	1090	kg/m ³	ISO 1183