

Technical Data Sheet



ALTECH PP-H FC 2030/100 GF30

MOCOM

Base Polymer	Polypropylene Homopolymer
Filler/Additive System	30 % glass fibres
Colour	natural color,white
Special Features	high stiffness,processing stabilised,easy release (demoulding),heat stabilised
Market Segment	packaging,Personal care,Machinery,electrical and electronic
Application Area	injection moulded parts,electrical components,domestic appliances,food contact
Typical Applications	kitchenware,functional components,housings

Pre-Drying Conditions	in an air circulating dryer 80-120 °C for 2-4 h in a dry air (dessiccant) dryer 80-120 °C for 2-3 h dependant on moisture content max. moisture content <0,10 %
Processing Injection Moulding	melt temperature 200-250 °C mould temperature 20-70 °C
Storage	dry, protected from light
Minimum Shelf Life	months <24

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	5100	MPa	ISO 178
Flexural Strength	90	MPa	ISO 178
Tensile Modulus	5800	MPa	ISO 527
Tensile Strength at Break	65	MPa	ISO 527
Tensile Elongation at Break	2	%	ISO 527
Impact Strength (Charpy, 23°C)	25	kJ/m²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	20	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	6	kJ/m²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	5.5	kJ/m²	ISO 179/1eA
Thermal Properties			
Vicat B50	122	°C	ISO 306
HDT / A (1,8 MPa)	140	°C	ISO 75-1/-2
DSC (Melt Point)	166	°C	ISO 11357
Rheological Properties			
Melt Index (MVR)	3.5	cm³/10min	ISO 1133
MVR temperature	230	°C	-

Technical Data Sheet



ALTECH PP-H FC 2030/100 GF30

MOCOM

MVR load	2.16	kg	-
Shrinkage (lengthwise, 24h)	0.2 - 0.4	%	ISO 294-4
Shrinkage (lateral, 24h)	0.3 - 0.5	%	ISO 294-4

Physical Properties

Density	1120	kg/m ³	ISO 1183
---------	------	-------------------	----------