

Technical Data Sheet



TEDUR L 9406-1



MOCOM

Base Polymer	Polyphenylene Sulphide
Filler/Additive System	10 % carbon fibres, 50 % glass fibre/mineral
Special Features	electrically conductive, high stiffness, low warpage
Market Segment	Automotive, Machinery
Application Area	injection moulded parts
Typical Applications	bearings and sliding elements, functional components

Pre-Drying Conditions in a dry air (dessiccant) dryer 130-140 °C
for 2-4 h
dependant on moisture content

Processing Injection Moulding melt temperature 320-340 °C
mould temperature >140 °C

Storage dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	23800	MPa	ISO 178
Flexural Strength	210	MPa	ISO 178
Flexural Deflection (Maximum Force)	1	%	ISO 178
Tensile Modulus	24500	MPa	ISO 527
Tensile Strength at Break	140	MPa	ISO 527
Tensile Elongation at Break	0.7	%	ISO 527
Impact Strength (Charpy, 23 °C)	17	kJ/m ²	ISO 179/1eU
Thermal Properties			
HDT / A (1,8 MPa)	280	°C	ISO 75-1/-2
DSC (Melt Point)	280	°C	ISO 11357
Electrical Properties			
Surface Resistance	150	Ohm	IEC 62631-3-2
Physical Properties			
Density	1830	kg/m ³	ISO 1183
Flammability			
Flammability (0.75 mm)	V-0	class	UL 94
Yellow Card available	yes	-	-