

Technical Data Sheet

❖ Alfater XL®



ALFATER XL A35I 2GP0050

MOCOM

Base Polymer	Thermoplastic Vulcanisate (PP+EPDM)
Colour	natural color
Service Temperature	max. range (depending on load, geometry, etc.) -40-125 °C
Special Features	good recovery, good weathering resistance, good chemical resistance, good ozone resistance, good hot air resistance, good hydrolysis resistant
Market Segment	Automotive, building and construction, do-it-yourself, electrical and electronic, Machinery, Furniture
Application Area	injection moulded parts
Typical Applications	seals, sealing lip, handles, soft touch elements, impact protection / shock absorber, protection caps, cable ducts, plugs, fastener & connector, 2K components
Adhesion to	Polypropylene Homopolymer, Polypropylene Copolymer, Polyethylene, Thermoplastic Vulcanisate (PP+EPDM), Thermoplastic Olefin Elastomer, Thermoplastic Elastomer general

Pre-Drying Conditions	in a dry air (dessiccant) dryer 60-70 °C for 2-4 h max. moisture content <0,10 %
Processing Injection Moulding	melt temperature 195-230 °C mould temperature 10-60 °C injection speed high back pressure (hydraulic) >5 bar holding pressure 50-70% of injection pressure
Storage	dry, protected from light not above 30°C tightly sealed do not stack the pallets
Minimum Shelf Life	months <12

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Tensile Stress at 100% Elongation (Type 2)	1.3	MPa	ISO 37
Tensile Strength (Type 2)	2.5	MPa	ISO 37
Tear Strength (Method Ba)	12	kN/m	ISO 34-1
Elongation at Break (Type 2)	250	%	ISO 37
Shore Hardness A (15s)	35	-	ISO 868
Thermal Properties			
Compression Set (22h / 100°C / 25% / Type A)	30	%	ISO 815
Compression Set (22h / 70°C / 25% / Type A)	27	%	ISO 815
Compression Set (72h / 22°C / 25% / Type A)	15	%	ISO 815

Technical Data Sheet

❖ Alfater XL[®]



ALFATER XL A35I 2GP0050

MOCOM

Compression Set (72h / 125 °C / 25% / Type A)	40	%	ISO 815
Electrical Properties			
Tracking Resistance (CTI)	600	-	IEC 60112
Rheological Properties			
Spiral Flow (2 mm wall thickness)	35	cm	-
Physical Properties			
Density	940	kg/m ³	ISO 1183
Ageing Properties			
Ozone resistance (method A)	passed	-	ISO 1431-1A

Diagrams

Viscosity-shear rate

