

Durethan® C38F 000000
PA*

Envalior

Film Extrusion, Unreinforced, Extrusion, Food Contact Quality, Transparent, Medium Viscosity, no additives

ISO 1043 PA*

Rheological properties	dry / cond	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	5 / *	cm³/10min	ISO 1133
Temperature	235 / *	°C	-
Load	2.16 / *	kg	-

Thermal Properties	dry / cond	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	212 / *	°C	ISO 11357-1/-3

Electrical Properties	dry / cond	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	- / 3	-	IEC 62631-2-1
Volume Resistivity	- / 1E11	Ohm*m	IEC 62631-3-1
Surface Resistivity	* / 1E11	Ohm	IEC 62631-3-2
Electric Strength	- / 30	kV/mm	IEC 60243-1

Other Properties	dry / cond	Unit	Test Standard
ISO Data			
Water Absorption	10 / *	%	Sim. to ISO 62
Humidity absorption	3 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m³	ISO 1183

Material Specific Properties	dry / cond	Unit	Test Standard
ISO Data			
Viscosity number	190 / *	cm³/g	ISO 307, 1157, 1628

Characteristics
Processing

Film Extrusion, Other Extrusion

Special Characteristics

Transparent

Delivery form

Pellets

Certifications

Food approval