

Durethan® BKV130H3.0 000000 DUS008
PA6-I-GF30

Envalior

Injection Molding, 30% Glass Reinforced, Heat Stabilized, Improved Impact

ISO 1043 PA6-I-GF30

Mechanical Properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	9000 / 5200	MPa	ISO 527
Stress at Break	160 / 100	MPa	ISO 527
Strain at Break	4 / 7	%	ISO 527
Impact Strength (Charpy), +23°C	95 / 110	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy), -30°C	80 / 80	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	18 / 28	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	10 / 10	kJ/m ²	ISO 179/1eA

Thermal Properties	dry / cond	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	222 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	205 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220 / *	°C	ISO 75-1/-2

Other Properties	dry / cond	Unit	Test Standard
ISO Data			
Density	1360 / -	kg/m ³	ISO 1183

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	280	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 6	h	-
Processing humidity	≤0.12	%	-
Melt temperature	260 - 290	°C	-
Mold temperature	80 - 100	°C	-

Characteristics
Processing

Injection Molding

Special Characteristics

Impact modified, Heat aging stabilized

Delivery form

Pellets

Injection Molding
PREPROCESSING

Residual moisture content: 0.03 - 0.12%

Drying temperature dry air dryer: 80 °C

Drying time dry air dryer 2 - 6 h

PROCESSING

Melt temperature (Tmin - Tmax): 260 - 290 °C

Mold temperature: 80 - 100 °C