

Durethan® BKV30XWPXT 901510
PA6-GF30

Envalior

Injection Molding, 30% Glass Reinforced, Heat Stabilized, Laser Weldable

ISO 1043 PA6-GF30

Rheological properties	dry / cond	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.2 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7 / *	%	ISO 294-4, 2577

Mechanical Properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	10000 / 5100	MPa	ISO 527
Stress at Break	170 / 90	MPa	ISO 527
Strain at Break	3.5 / 7.5	%	ISO 527
Impact Strength (Charpy), +23°C	70 / 95	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy), -30°C	55 / 60	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	10 / 20	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	8 / 7	kJ/m ²	ISO 179/1eA
Puncture - maximum force, +23°C	800 / -	N	ISO 6603-2
Puncture energy, +23°C	2.8 / -	J	ISO 6603-2

Thermal Properties	dry / cond	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	218 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	200 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	216 / *	°C	ISO 75-1/-2
Coeff. of Linear Therm. Expansion, parallel	20 / *	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	100 / *	E-6/K	ISO 11359-1/-2

Other Properties	dry / cond	Unit	Test Standard
ISO Data			
Humidity absorption	2.7 / *	%	Sim. to ISO 62
Density	1370 / -	kg/m ³	ISO 1183

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	280	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294


Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 6	h	-
Processing humidity	≤0.12	%	-
Melt temperature	270 - 290	°C	-
Mold temperature	80 - 120	°C	-

Durethan® BKV30XWPXT 901510 PA6-GF30


Envalior

Diagrams


Stress-strain




Stress-strain



Secant modulus-strain



Secant modulus-strain



Characteristics

Processing

Injection Molding

Delivery form

Pellets

Injection Molding

PREPROCESSING

Special Characteristics

Heat aging stabilized

Durethan® BKV30XWPXT 901510
PA6-GF30

Envalior

Residual moisture content: 0.03 - 0.12%

Drying temperature dry air dryer: 80 °C

Drying time dry air dryer 2 - 6 h

PROCESSING

Melt temperature (Tmin - Tmax): 270 - 290 °C

Mold temperature: 80 - 120 °C
