

Ultramid® B3E2G3
PA6-GF15

BASF

Mechanical Properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	5500 / 3200	MPa	ISO 527
Stress at Break	125 / 75	MPa	ISO 527
Strain at Break	3 / 11	%	ISO 527
Impact Strength (Charpy), +23°C	45 / 100	kJ/m²	ISO 179/1eU
Impact Strength (Charpy), -30°C	35 / -	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	7 / 11	kJ/m²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	6 / -	kJ/m²	ISO 179/1eA

Thermal Properties	dry / cond	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	190 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	210 / *	°C	ISO 75-1/-2

Electrical Properties	dry / cond	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	3.5 / 6	-	IEC 62631-2-1
Dissipation Factor, 1MHz	200 / 2500	E-4	IEC 62631-2-1
Volume Resistivity	1E13 / 1E10	Ohm*m	IEC 62631-3-1
Comparative tracking index	550 / -	-	IEC 60112

Other Properties	dry / cond	Unit	Test Standard
ISO Data			
Water Absorption	8.7 / *	%	Sim. to ISO 62
Humidity absorption	2 / *	%	Sim. to ISO 62
Density	1230 / -	kg/m³	ISO 1183
Bulk density	700	kg/m³	-

Material Specific Properties	dry / cond	Unit	Test Standard
ISO Data			
Viscosity number	145 / *	cm³/g	ISO 307, 1157, 1628

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	260 - 280	°C	-
Mold temperature	80 - 100	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Applications

Automotive, Building Construction, IT / Business Machine,
Electrical and Electronical