

Ultramid® B3UG4

PA6-GF20 FR(30)

BASF

Without halogens and phosphorous flame retardant glass fiber reinforced injection moulding grade with outstanding flowability properties, good electrical properties and low smoke density. The product is resistant to the glow wire test GWFI up to 960 °C. Due to the halide free stabilization the impact on corrosion is minimized and sensitive electronic components are better protected.

Rheological properties	dry / cond	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	80 / *	cm³/10min	ISO 1133
Temperature	275 / *	°C	-
Load	5 / *	kg	-
Molding shrinkage, parallel	0.8 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8 / *	%	ISO 294-4, 2577

Mechanical Properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	6000 / 3000	MPa	ISO 527
Stress at Break	95 / 50	MPa	ISO 527
Strain at Break	3 / 6	%	ISO 527
Tensile Creep Modulus, 1000h	* / 1500	MPa	ISO 899-1
Impact Strength (Charpy), +23°C	40 / 110	kJ/m²	ISO 179/1eU
Impact Strength (Charpy), -30°C	35 / -	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	3 / 9	kJ/m²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	3.4 / -	kJ/m²	ISO 179/1eA

Thermal Properties	dry / cond	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	170 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	210 / *	°C	ISO 75-1/-2
Coeff. of Linear Therm. Expansion, parallel	41 / *	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	86 / *	E-6/K	ISO 11359-1/-2
Burning Behav. at 1.5 mm Nom. Thickn.	V-2 / *	class	UL 94
Thickness tested	1.5 / *	mm	-
UL recognition	yes / *	-	-
Burning Behav. at thickness h	V-2 / *	class	UL 94
Thickness tested	0.7 / *	mm	-
UL recognition	yes / *	-	-
Oxygen index	31 / *	%	ISO 4589-1/-2

Electrical Properties	dry / cond	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	3.8 / -	-	IEC 62631-2-1
Dissipation Factor, 1MHz	150 / -	E-4	IEC 62631-2-1
Volume Resistivity	1E13 / 1E9	Ohm*m	IEC 62631-3-1
Surface Resistivity	* / 1E12	Ohm	IEC 62631-3-2
Electric Strength	35 / 34	kV/mm	IEC 60243-1
Comparative tracking index	- / 550	-	IEC 60112

Other Properties	dry / cond	Unit	Test Standard
ISO Data			
Water Absorption	6.9 / *	%	Sim. to ISO 62
Humidity absorption	2.2 / *	%	Sim. to ISO 62
Density	1310 / -	kg/m³	ISO 1183

Material Specific Properties	dry / cond	Unit	Test Standard
ISO Data			
Viscosity number	150 / *	cm³/g	ISO 307, 1157, 1628

Rheological calculation properties	Value	Unit	Test Standard
ISO Data			
Ejection temperature	160	°C	-

Ultramid® B3UG4

PA6-GF20 FR(30)


BASF

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	270	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.15	%	-
Melt temperature	250 - 275	°C	-
Mold temperature	80 - 90	°C	-

Diagrams


Viscosity-shear rate




Shearstress-shear rate



Stress-strain




Stress-strain




Ultramid® B3UG4
PA6-GF20 FR(30)

BASF


Secant modulus-strain




Secant modulus-strain



Stress-strain (isochronous) 23 °C




Creep modulus-time 23 °C




Ultramid® B3UG4
PA6-GF20 FR(30)

BASF


Stress-strain (isochronous) 60°C




Creep modulus-time 60°C



Stress-strain (isochronous) 90°C




Creep modulus-time 90°C




Ultramid® B3UG4
PA6-GF20 FR(30)

BASF


Stress-strain (isochronous) 120°C




Creep modulus-time 120°C



Specific volume-temperature (pvT)



Tensile Modulus-Temperature




Ultramid® B3UG4

PA6-GF20 FR(30)

BASF

Tensile Modulus-Temperature



Characteristics

Processing

Injection Molding

Additives

Release agent

Delivery form

Pellets

Special Characteristics

Flame retardant, Halogen-free, Heat aging stabilized

Injection Molding

PREPROCESSING

Pre/Post-processing, max. allowed water content: .15 %

Pre/Post-processing, Pre-drying, Temperature: 80 °C

Pre/Post-processing, Pre-drying, Time: 4 h

PROCESSING

injection molding, Melt temperature, range: 250 - 275 °C

injection molding, Melt temperature, recommended: 270 °C

injection molding, Mold temperature, range: 80 - 90 °C

injection molding, Mold temperature, recommended: 80 °C

injection molding, Dwell time, thermoplastics: 10 min

Chemical Media Resistance

Acids

✓ Acetic Acid (5% by mass) (23°C)