

Ultramid® B3WG6 HP bk23210
PA6-GF30

BASF

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	50	cm ³ /10min	ISO 1133
Temperature	275	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1360	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Special Characteristics

Heat aging stabilized

Delivery form

Pellets, Black

Applications

Automotive