

Pocan® BF4235 000000
PBT-GF30 FR(17)

Envalior

Injection Molding, 30% Glass Reinforced, Flame Retardant

ISO 1043 PBT-GF30 FR(17)

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	14	cm³/10min	ISO 1133
Temperature	260	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.4	%	ISO 294-4, 2577
Molding shrinkage, normal	1.1	%	ISO 294-4, 2577

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	11000	MPa	ISO 527
Stress at Break	135	MPa	ISO 527
Strain at Break	2.1	%	ISO 527
Tensile Creep Modulus, 1h	11000	MPa	ISO 899-1
Tensile Creep Modulus, 1000h	10000	MPa	ISO 899-1
Impact Strength (Charpy), +23°C	50	kJ/m²	ISO 179/1eU
Impact Strength (Charpy), -30°C	50	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	10	kJ/m²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	10	kJ/m²	ISO 179/1eA

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	225	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	205	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75-1/-2
Coeff. of Linear Therm. Expansion, parallel	20	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	90	E-6/K	ISO 11359-1/-2
Burning Behav. at 1.5 mm Nom. Thickn.	V-0	class	UL 94
Burning Behav. 5V at Thickness h	5VA	class	IEC 60695-11-20
Thickness tested	1.5	mm	-
Oxygen index	32	%	ISO 4589-1/-2

Electrical Properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 100Hz	4	-	IEC 62631-2-1
Relative permittivity, 1MHz	3.9	-	IEC 62631-2-1
Dissipation Factor, 100Hz	50	E-4	IEC 62631-2-1
Dissipation Factor, 1MHz	160	E-4	IEC 62631-2-1
Volume Resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface Resistivity	>1E15	Ohm	IEC 62631-3-2
Electric Strength	29	kV/mm	IEC 60243-1
Comparative tracking index	200	-	IEC 60112

Other Properties	Value	Unit	Test Standard
ISO Data			
Water Absorption	0.4	%	Sim. to ISO 62
Humidity absorption	0.1	%	Sim. to ISO 62
Density	1660	kg/m³	ISO 1183

Material Specific Properties	Value	Unit	Test Standard
ISO Data			
Viscosity number	93	cm³/g	ISO 307, 1157, 1628

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	250	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

Pocan® BF4235 000000


PBT-GF30 FR(17)

Envalior


Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4 - 8	h	-
Processing humidity	≤0.02	%	-
Melt temperature	240 - 260	°C	-
Mold temperature	80 - 100	°C	-

Diagrams

Viscosity-shear rate



Shearstress-shear rate



Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

Flame retardant, Heat aging stabilized

Injection Molding

PREPROCESSING

Residual moisture content: 0.00 - 0.02 %

Drying temperature circulating air dryer: 120 °C

Drying time circulating air dryer: 4 - 8 h

PROCESSING

Melt temperature (Tmin - Tmax): 240 - 260 °C

Mold temperature: 80 - 100 °C