

Pocan® S7926 000000

PBT-I FR(17)

Envalior

Injection Molding, Unreinforced, Extrusion, Flame Retardant, Improved Impact

ISO 1043 PBT-I FR(17)

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	40	cm ³ /10min	ISO 1133
Temperature	270	°C	-
Load	5	kg	-
Molding shrinkage, parallel	2.1	%	ISO 294-4, 2577
Molding shrinkage, normal	2.0	%	ISO 294-4, 2577

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2400	MPa	ISO 527
Yield stress	40	MPa	ISO 527
Yield strain	3	%	ISO 527
Tensile Creep Modulus, 1h	2300	MPa	ISO 899-1
Tensile Creep Modulus, 1000h	1500	MPa	ISO 899-1
Impact Strength (Charpy), +23°C	no break	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy), -30°C	no break	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	12	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	10	kJ/m ²	ISO 179/1eA

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	225	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	60	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	130	°C	ISO 75-1/-2
Coeff. of Linear Therm. Expansion, parallel	110	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	120	E-6/K	ISO 11359-1/-2
Burning Behav. at 1.5 mm Nom. Thickn.	V-0	class	UL 94
Burning Behav. 5V at Thickness h	5VA	class	IEC 60695-11-20
Thickness tested	3.0	mm	-
Oxygen index	30	%	ISO 4589-1/-2

Electrical Properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 100Hz	3.2	-	IEC 62631-2-1
Relative permittivity, 1MHz	3.1	-	IEC 62631-2-1
Dissipation Factor, 100Hz	15	E-4	IEC 62631-2-1
Dissipation Factor, 1MHz	150	E-4	IEC 62631-2-1
Volume Resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface Resistivity	>1E15	Ohm	IEC 62631-3-2
Electric Strength	30	kV/mm	IEC 60243-1
Comparative tracking index	600	-	IEC 60112

Other Properties	Value	Unit	Test Standard
ISO Data			
Water Absorption	0.4	%	Sim. to ISO 62
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1370	kg/m ³	ISO 1183

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	250	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4 - 8	h	-


Pocan® S7926 000000
PBT-I FR(17)

Envalior


Processing humidity	≤0.02	%	-
Melt temperature	240 - 260	°C	-
Mold temperature	80 - 100	°C	-

Diagrams


Viscosity-shear rate




Shearstress-shear rate



Stress-strain




Secant modulus-strain




Pocan® S7926 000000
PBT-I FR(17)

Envalior


Stress-strain (isochronous) 23°C




Creep modulus-time 23°C



Stress-strain (isochronous) 40°C



Creep modulus-time 40°C




Pocan® S7926 000000


PBT-I FR(17)

Envalior

Stress-strain (isochronous) 60 °C



Creep modulus-time 60 °C



Characteristics

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets

Special Characteristics

Flame retardant, Impact modified, Heat aging stabilized

Injection Molding

PREPROCESSING

Residual moisture content: 0.00 - 0.02 %

Drying temperature circulating air dryer: 120 °C

Drying time circulating air dryer: 4 - 8 h

PROCESSING

Melt temperature (Tmin - Tmax): 240 - 260 °C

Mold temperature: 80 - 100 °C