

Ultradur® B 4300 G10

PBT-GF50

BASF

具有50 %玻璃纤维的注塑等级，用于非常坚硬的技术零部件（例如PCB和小型电动机罩）。

The products can also be offered as BMBcert™ and/or Ccycled™. Due to the Massbalance approach the product properties do not change.

Abbreviated designation according to ISO 1043: PBT-GF50

流变性能	数值	单位	试验方法
ISO数据			
熔体体积流动速度, MVR	3.5	cm³/10min	ISO 1133
温度	250	°C	-
载荷	2.16	kg	-
模塑收缩率, 平行	0.4	%	ISO 294-4, 2577
模塑收缩率, 垂直	1.0	%	ISO 294-4, 2577

机械性能	数值	单位	试验方法
ISO数据			
拉伸模量	16500	MPa	ISO 527
断裂应力	160	MPa	ISO 527
断裂伸长率	1.7	%	ISO 527
无缺口简支梁冲击强度, +23°C	60	kJ/m²	ISO 179/1eU
无缺口简支梁冲击强度, -30°C	70	kJ/m²	ISO 179/1eU
简支梁缺口冲击强度, +23°C	11	kJ/m²	ISO 179/1eA
简支梁缺口冲击强度, -30°C	10	kJ/m²	ISO 179/1eA

热性能	数值	单位	试验方法
ISO数据			
熔融温度, 10°C/min	223	°C	ISO 11357-1/-3
热变形温度, 1.80 MPa	210	°C	ISO 75-1/-2
热变形温度, 0.45 MPa	220	°C	ISO 75-1/-2
线性热膨胀系数, 平行	20	E-6/K	ISO 11359-1/-2
线性热膨胀系数, 垂直	95	E-6/K	ISO 11359-1/-2
1.5mm名义厚度时的燃烧性	HB	class	UL 94
测试用试样的厚度	1.5	mm	-
UL注册	是的	-	-
厚度为h时的燃烧性	HB	class	UL 94
测试用试样的厚度	0.8	mm	-
UL注册	是的	-	-
燃烧性 - 氧指数	19.5	%	ISO 4589-1/-2

电性能	数值	单位	试验方法
ISO数据			
相对介电常数, 100Hz	4	-	IEC 62631-2-1
相对介电常数, 1MHz	4	-	IEC 62631-2-1
介质损耗因子, 100Hz	12	E-4	IEC 62631-2-1
介质损耗因子, 1MHz	150	E-4	IEC 62631-2-1
体积电阻率	>1E13	Ohm*m	IEC 62631-3-1
表面电阻率	1E13	Ohm	IEC 62631-3-2
介电强度	37	kV/mm	IEC 60243-1
相对漏电起痕指数	425	-	IEC 60112

其它性能	数值	单位	试验方法
ISO数据			
吸水性	0.4	%	类似ISO 62
吸湿性	0.2	%	类似ISO 62
密度	1730	kg/m³	ISO 1183

模塑测量的特殊性能	数值	单位	试验方法
ISO数据			
粘数.	97	cm³/g	ISO 307, 1157, 1628

Ultradur® B 4300 G10
PBT-GF50

BASF


流变计算用参数	数值	单位	试验方法
ISO数据			
喷射温度	185	°C	-

试样制备条件	数值	单位	试验方法
ISO数据			
注塑, 熔体温度	270	°C	ISO 294
注塑, 模具温度	80	°C	ISO 294
注塑, 注射速度	200	mm/s	ISO 294


加工推荐 (注塑)	数值	单位	试验方法
预干燥-温度	80 - 120	°C	-
预干燥-时间	4	h	-
加工湿度	≤ 0.04	%	-
注塑熔体温度	260 - 275	°C	-
模具温度	80 - 120	°C	-

函数

粘度 - 剪切速度




剪切应力 - 剪切速度




Ultradur® B 4300 G10
PBT-GF50

BASF


动态剪切模量 - 温度




应力 - 应变.



正割模量 - 应变.




应力 - 应变(等时的) 23°C




Ultradur® B 4300 G10
PBT-GF50

BASF


蠕变模量 - 时间. 23°C




应力 - 应变(等时的) 40°C



蠕变模量 - 时间. 40°C




应力 - 应变(等时的) 90°C




Ultradur® B 4300 G10
PBT-GF50

BASF


蠕变模量 - 时间. 90°C




应力 - 应变(等时的) 120°C



蠕变模量 - 时间. 120°C



应力 - 应变(等时的) 160°C




Ultradur® B 4300 G10


PBT-GF50

BASF


蠕变模量 - 时间, 160°C




比容 - 温度(pvT)



拉伸模量 - 温度



线性热膨胀系数(垂直)



特征

加工方法

注塑

供货形式

粒料

添加剂

润滑剂

特殊性能

经光稳处理的/耐光的, 经耐紫外线处理的/耐气候的,
经热稳处理的/耐热的

注塑

PREPROCESSING

Pre/Post-processing, max. allowed water content: .04 %
Pre/Post-processing, Pre-drying, Temperature: 80 - 120 °C
Pre/Post-processing, Pre-drying, Time: 4 h

PROCESSING

injection molding, Melt temperature, range: 260 - 275 °C
injection molding, Melt temperature, recommended: 270 °C
injection molding, Mold temperature, range: 80 - 120 °C

Ultradur® B 4300 G10

PBT-GF50

BASF

injection molding, Mold temperature, recommended: 80 °C

耐化学性

酸类

- ✓ 醋酸 (5g/100g) (23°C)