

Ultradur® B 4300 G4 FC Aqua BK15136

PBT-GF20

BASF

Ultradur® B 4300 G4 FC Aqua bk15136 is suitable for plastic parts, where material approval regarding drinking water contact and direct food contact is a mandatory requirement.

The product is approved according to

- 21 CFR FDA §177.1660 "Poly(tetramethylene terephthalate)";
- European Food Contact European Food Contact Commission Regulation (EU) 10/2011;
- GMP (EC) N°2023/2006;

and suitable for drinking water contact in accordance with

- KTW-BWGL;
- WRAS (approval);
- ACS (disclosure of ingredients);
- NSF (disclosure of ingredients).

For questions regarding the compliance with further regulations, and certificates, please contact your local BASF representative or Plastics Safety (E-Mail: plastics.safety@basf.com).

The products can also be offered as BMBcert™ and/or Ccycled™. Due to the Massbalance approach the product properties do not change.

Abbreviated designation according to ISO 1043: PBT-GF20

流变性能	数值	单位	试验方法
ISO数据			
熔体体积流动速度, MVR	16	cm³/10min	ISO 1133
温度	250	°C	-
载荷	2.16	kg	-
模塑收缩率, 平行	0.4	%	ISO 294-4, 2577
模塑收缩率, 垂直	1.2	%	ISO 294-4, 2577

机械性能	数值	单位	试验方法
ISO数据			
拉伸模量	7000	MPa	ISO 527
断裂应力	120	MPa	ISO 527
断裂伸长率	3.5	%	ISO 527
无缺口简支梁冲击强度, +23°C	53	kJ/m²	ISO 179/1eU
无缺口简支梁冲击强度, -30°C	47	kJ/m²	ISO 179/1eU
简支梁缺口冲击强度, +23°C	6	kJ/m²	ISO 179/1eA
简支梁缺口冲击强度, -30°C	6	kJ/m²	ISO 179/1eA

热性能	数值	单位	试验方法
ISO数据			
熔融温度, 10°C/min	223	°C	ISO 11357-1/-3
热变形温度, 1.80 MPa	195	°C	ISO 75-1/-2
热变形温度, 0.45 MPa	220	°C	ISO 75-1/-2
线性热膨胀系数, 平行	35	E-6/K	ISO 11359-1/-2
线性热膨胀系数, 垂直	125	E-6/K	ISO 11359-1/-2
1.5mm名义厚度时的燃烧性	HB	class	UL 94
测试用试样的厚度	1.5	mm	-
UL注册	是的	-	-
UL注册	是的	-	-
燃烧性 - 氧指数	19.5	%	ISO 4589-1/-2

电性能	数值	单位	试验方法
ISO数据			
介质损耗因子, 100Hz	23	E-4	IEC 62631-2-1
介质损耗因子, 1MHz	190	E-4	IEC 62631-2-1
表面电阻率	>1E15	Ohm	IEC 62631-3-2
介电强度	37	kV/mm	IEC 60243-1
相对漏电起痕指数	275	-	IEC 60112

Ultradur® B 4300 G4 FC Aqua BK15136

PBT-GF20

BASF

其它性能	数值	单位	试验方法
ISO数据			
吸水性	0.4	%	类似ISO 62
吸湿性	0.2	%	类似ISO 62
密度	1450	kg/m³	ISO 1183

模塑测量的特殊性能	数值	单位	试验方法
ISO数据			
粘数	105	cm³/g	ISO 307, 1157, 1628

流变计算用参数	数值	单位	试验方法
ISO数据			
熔体密度	1190	kg/m³	-
熔体	0.19	W/(m K)	-
熔体的比热	1890	J/(kg K)	-
喷射温度	175	°C	-

试样制备条件	数值	单位	试验方法
ISO数据			
注塑, 熔体温度	260	°C	ISO 294
注塑, 模具温度	80	°C	ISO 294
注塑, 注射速度	200	mm/s	ISO 294

加工推荐 (注塑)	数值	单位	试验方法
预干燥-温度	80 - 120	°C	-
预干燥-时间	4	h	-
加工湿度	≤ 0.04	%	-
注塑熔体温度	250 - 275	°C	-
模具温度	60 - 100	°C	-

特征

加工方法

注塑

供货形式

粒料, 黑色

添加剂

润滑剂

特殊性能

经光稳处理的/耐光的, 经耐紫外线处理的/耐气候的, 经热稳处理的/耐热的

生态估价

食物接触声明, 10/2011认证, FDA 21 CFR认证, 与饮用水接触的塑料材料, 可水接触的(KTW), 可水接触的(DVGW W270), NSF认证

注塑

PREPROCESSING

Pre/Post-processing, max. allowed water content: .04 %
Pre/Post-processing, Pre-drying, Temperature: 80 - 120 °C
Pre/Post-processing, Pre-drying, Time: 4 h

PROCESSING

injection molding, Melt temperature, range: 250 - 275 °C
injection molding, Melt temperature, recommended: 260 °C
injection molding, Mold temperature, range: 60 - 100 °C
injection molding, Mold temperature, recommended: 80 °C

耐化学性

酸类

✓ 醋酸 (5g/100g) (23°C)

权利义务的法律声明