

Ultradur® B 4300 G4 LS High Speed BK15045
PBT-GF20

BASF

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	28	cm³/10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	7050	MPa	ISO 527
Stress at Break	115	MPa	ISO 527
Strain at Break	3	%	ISO 527

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	223	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	200	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75-1/-2

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1450	kg/m³	ISO 1183

Characteristics

Processing

Injection Molding

Features

Laser Markable, Low Warpage

Delivery form

Black