

Ultradur® B 4315 G6 HR BK 15045
PBT-GF30

BASF

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	15	cm³/10min	ISO 1133
Temperature	275	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Molding shrinkage, normal	1.1	%	ISO 294-4, 2577

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	9550	MPa	ISO 527
Stress at Break	130	MPa	ISO 527
Strain at Break	3.2	%	ISO 527
Impact Strength (Charpy), +23°C	77	kJ/m²	ISO 179/1eU
Impact Strength (Charpy), -30°C	68	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	10	kJ/m²	ISO 179/1eA

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	223	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	208	°C	ISO 75-1/-2
Burning Behav. at 1.5 mm Nom. Thickn.	HB	class	UL 94
Thickness tested	1.6	mm	-

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1510	kg/m³	ISO 1183
Bulk density	750	kg/m³	-

Material Specific Properties	Value	Unit	Test Standard
ISO Data			
Viscosity number	102	cm³/g	ISO 307, 1157, 1628

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	250 - 280	°C	-
Mold temperature	60 - 100	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Black

Features

Laser Markable, Low Odor

Chemical Resistance

Hydrolysis

Applications

Automotive, Electrical and Electronical