

Koattro PB M 1200M

PB...

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	1200	g/10min	ISO 1133
MFI temperature	190	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Flexural Modulus (23°C)	340	MPa	ISO 178

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	908	kg/m³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	150 - 220	°C	-

Characteristics

Processing

Injection Molding

Applications

Packaging

Features

Blending Resin, Good Adhesion, Thermal Stability, Copolymer,
Random Copolymer