



Bayblend® T70 X RE

(PC+ABS)

Covestro Deutschland AG

- (PC+ABS)-Blend
- General Purpose Grade
- Vicat/B 120 temperature = 124 °C
- good injection molding processing behaviour (easy flowing)
- excellent long-term ageing behaviour under humid conditions
- good painting performance
- improved chemical resistance
- low VOC emissions and odour

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	18	cm ³ /10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.8	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8	%	ISO 294-4, 2577

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2250	MPa	ISO 527
Yield stress	53	MPa	ISO 527
Yield strain	4.7	%	ISO 527
Nominal strain at break	>50	%	ISO 527
Impact Strength (Charpy), +23°C	no break	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy), -30°C	no break	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	60	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	50	kJ/m ²	ISO 179/1eA
Puncture - maximum force, +23°C	4300	N	ISO 6603-2
Puncture - maximum force, -30°C	5200	N	ISO 6603-2
Puncture energy, +23°C	48	J	ISO 6603-2
Puncture energy, -30°C	53	J	ISO 6603-2
Notched Impact Strength (Izod), 23°C	55	kJ/m ²	ISO 180/1A
Notched Impact Strength (Izod)	45	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Impact Strength (Izod), 23°C	no break	kJ/m ²	ISO 180/1U

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (1.80 MPa)	103	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	125	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	122	°C	ISO 306
Coeff. of Linear Therm. Expansion, parallel	70	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	70	E-6/K	ISO 11359-1/-2
Burning Behav. at thickness h	HB	class	UL 94
Thickness tested	0.8	mm	-

Electrical Properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 100Hz	2.9	-	IEC 62631-2-1
Relative permittivity, 1MHz	3	-	IEC 62631-2-1
Dissipation Factor, 100Hz	25	E-4	IEC 62631-2-1
Dissipation Factor, 1MHz	90	E-4	IEC 62631-2-1
Volume Resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface Resistivity	>1E15	Ohm	IEC 62631-3-2
Electric Strength	40	kV/mm	IEC 60243-1
Comparative tracking index	200	-	IEC 60112

Other Properties	Value	Unit	Test Standard
ISO Data			
Water Absorption	0.4	%	Sim. to ISO 62
Humidity absorption	0.1	%	Sim. to ISO 62
Density	1130	kg/m ³	ISO 1183

Bayblend® T70 X RE
(PC+ABS)

Covestro Deutschland AG

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	280	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294
Injection Molding, injection velocity	240	mm/s	ISO 294

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	95 - 110	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.01	%	-
Melt temperature	270 - 290	°C	-
Mold temperature	70 - 90	°C	-

Characteristics

Processing

Injection Molding

Certifications

Contains renewable resources, ISCC Plus

Features

Low Emission, Low Odor

Applications

General Purpose

Chemical Resistance

General Chemical Resistance