



Bayblend® FR3016 W

PC-I FR(40)

Covestro Deutschland AG

- (PC-I)-Blend
- flame retardant
- Vicat/B 120 temperature = 101 °C
- UL-recognition 94 V-0 at 0.75mm
- rated f1 per UL746 C "Outdoor Suitability"
- improved colorability compared to other PC+ASA grades

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	32	cm ³ /10min	ISO 1133
Temperature	240	°C	-
Load	5	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2700	MPa	ISO 527
Yield stress	64	MPa	ISO 527
Yield strain	4.1	%	ISO 527
Nominal strain at break	>50	%	ISO 527
Flexural Modulus (23 °C)	2700	MPa	ISO 178
Flexural strength	102	MPa	ISO 178
Notched Impact Strength (Izod), 23 °C	12	kJ/m ²	ISO 180/1A
Notched Impact Strength (Izod)	5	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Impact Strength (Izod), 23 °C	no break	kJ/m ²	ISO 180/1U

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (1.80 MPa)	83	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	93	°C	ISO 75-1/-2
Vicat softening temperature, 50 °C/h 50N	98	°C	ISO 306
Coeff. of Linear Therm. Expansion, parallel	65	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	65	E-6/K	ISO 11359-1/-2
Burning Behav. at thickness h	V-0	class	UL 94
Thickness tested	0.8	mm	-

Electrical Properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 100Hz	3.2	-	IEC 62631-2-1
Relative permittivity, 1MHz	3.1	-	IEC 62631-2-1
Volume Resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface Resistivity	>1E15	Ohm	IEC 62631-3-2
Electric Strength	35	kV/mm	IEC 60243-1

Other Properties	Value	Unit	Test Standard
ISO Data			
Water Absorption	0.5	%	Sim. to ISO 62
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1210	kg/m ³	ISO 1183

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	240	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294
Injection Molding, injection velocity	240	mm/s	ISO 294

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	240 - 270	°C	-

Bayblend® FR3016 W

PC-I FR(40)

Covestro Deutschland AG

Mold temperature	60 - 90	°C	-
Zone 1	220 - 230	°C	-
Zone 2	225 - 235	°C	-
Zone 3	230 - 240	°C	-
Nozzle temperature	255 - 265	°C	-
Back pressure	5 - 15	MPa	-

Characteristics

Processing

Injection Molding

Special Characteristics

Flame retardant, Impact modified, UV stablized