



Makrolon® 6165 X RE

PC FR

Covestro Deutschland AG

- MVR (300 °C/1.2 kg) 28 cm³/10 min
- flame retardant
- UL 94V-0/1.2 mm
- low viscosity
- easy release

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	28	cm³/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577
Melt Flow Index, MFI	30	g/10min	ISO 1133
MFI temperature	300	°C	-
MFI load	1.2	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2350	MPa	ISO 527
Yield stress	65	MPa	ISO 527
Yield strain	6	%	ISO 527
Nominal strain at break	>50	%	ISO 527
Impact Strength (Charpy), +23°C	no break	kJ/m²	ISO 179/1eU
Puncture - maximum force, +23°C	4800	N	ISO 6603-2
Puncture energy, +23°C	45	J	ISO 6603-2
Notched Impact Strength (Izod), 23°C	15	kJ/m²	ISO 180/1A
Notched Impact Strength (Izod)	11	kJ/m²	ISO 180/1A
Temperature	-30	°C	-

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (1.80 MPa)	124	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	136	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	143	°C	ISO 306
Coeff. of Linear Therm. Expansion, parallel	65	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	65	E-6/K	ISO 11359-1/-2
Burning Behav. at thickness h	V-0	class	UL 94
Thickness tested	1.2	mm	-
Oxygen index	35	%	ISO 4589-1/-2
Glow Wire (GWFI, Flammability Index)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	1.5	mm	-
Glow Wire (GWFI, Flammability Index)	960	°C	IEC 60695-2-12
GWFI - thickness tested (2)	3	mm	-

Electrical Properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 100Hz	3.1	-	IEC 62631-2-1
Relative permittivity, 1MHz	3	-	IEC 62631-2-1
Volume Resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface Resistivity	>1E15	Ohm	IEC 62631-3-2
Electric Strength	34	kV/mm	IEC 60243-1
Comparative tracking index	225	-	IEC 60112

Other Properties	Value	Unit	Test Standard
ISO Data			
Water Absorption	0.3	%	Sim. to ISO 62
Humidity absorption	0.12	%	Sim. to ISO 62
Density	1200	kg/m³	ISO 1183
Bulk density	640	kg/m³	-

Makrolon® 6165 X RE

PC FR

Covestro Deutschland AG

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	280	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	2 - 3	h	-
Processing humidity	≤0.02	%	-
Melt temperature	280 - 320	°C	-
Mold temperature	80 - 120	°C	-
Zone 1	250 - 260	°C	-
Zone 2	270 - 280	°C	-
Zone 3	280 - 290	°C	-
Nozzle temperature	290 - 300	°C	-
Back pressure	5 - 15	MPa	-

Characteristics

Processing

Injection Molding

Special Characteristics

Flame retardant, Opaque

Additives

Release agent

Certifications

Contains renewable resources, ISCC Plus