



Makrolon® Ai2497

PC

Covestro Deutschland AG

- MVR (300 °C/1.2 kg) 19 cm³/10 min
- UV stabilized
- easy release
- Automotive interior
- developed for high-gloss surfaces with highest requirements

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	19	cm³/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2400	MPa	ISO 527
Yield stress	64	MPa	ISO 527
Yield strain	6	%	ISO 527
Nominal strain at break	>50	%	ISO 527
Impact Strength (Charpy), +23°C	no break	kJ/m²	ISO 179/1eU
Flexural Modulus (23°C)	2350	MPa	ISO 178
Flexural strength	98	MPa	ISO 178
Notched Impact Strength (Izod), 23°C	65	kJ/m²	ISO 180/1A
Notched Impact Strength (Izod)	15	kJ/m²	ISO 180/1A
Temperature	-30	°C	-

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (1.80 MPa)	124	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	136	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	141	°C	ISO 306
Coeff. of Linear Therm. Expansion, parallel	65	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	65	E-6/K	ISO 11359-1/-2

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1200	kg/m³	ISO 1183

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	280	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Melt temperature	280 - 320	°C	-
Mold temperature	80	°C	-
Injection speed	200	mm/s	-

Characteristics

Processing	Special Characteristics
Injection Molding	UV stabilized, Opaque

Delivery form	Features
Black	High Gloss

Additives	Applications
Release agent	Automotive