



Makrolon® Ai2215 EL
PC

Covestro Deutschland AG

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	34	cm³/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2200	MPa	ISO 527
Yield stress	63	MPa	ISO 527
Yield strain	6	%	ISO 527
Nominal strain at break	>50	%	ISO 527
Stress at Break	60	MPa	ISO 527
Strain at Break	125	%	ISO 527
Impact Strength (Charpy), -30°C	no break	kJ/m²	ISO 179/1eU
Puncture - maximum force, +23°C	4900	N	ISO 6603-2
Puncture - maximum force, -30°C	5900	N	ISO 6603-2
Puncture energy, +23°C	50	J	ISO 6603-2
Puncture energy, -30°C	55	J	ISO 6603-2
Notched Impact Strength (Izod), 23°C	55	kJ/m²	ISO 180/1A
Notched Impact Strength (Izod)	13	kJ/m²	ISO 180/1A
Temperature	-20	°C	-

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Glass Transition Temperature (10°C/min)	145	°C	ISO 11357-1/-2
Temp. of deflection under load (1.80 MPa)	125	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	138	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	145	°C	ISO 306
Coeff. of Linear Therm. Expansion, parallel	67	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	67	E-6/K	ISO 11359-1/-2
Oxygen index	28	%	ISO 4589-1/-2

Other Properties	Value	Unit	Test Standard
ISO Data			
Water Absorption	0.3	%	Sim. to ISO 62
Humidity absorption	0.12	%	Sim. to ISO 62
Density	1190	kg/m³	ISO 1183
Bulk density	660	kg/m³	-

Film Properties	Value	Unit	Test Standard
ISO Data			
Haze	13	-	ISO 14782

Material Specific Properties	Value	Unit	Test Standard
ISO Data			
Luminous transmittance	85	%	ISO 13468-1, -2

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	280	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	2 - 3	h	-
Processing humidity	≤0.02	%	-

Makrolon® Ai2215 EL
PC

Covestro Deutschland AG

Melt temperature	250 - 300	°C	-
Mold temperature	80 - 120	°C	-
Zone 1	230 - 240	°C	-
Zone 2	250 - 260	°C	-
Zone 3	260 - 270	°C	-
Nozzle temperature	260 - 270	°C	-
Back pressure	5 - 15	MPa	-

Characteristics

Processing

Injection Molding

Special Characteristics

Transparent

Delivery form

Pellets

Features

Light Guiding

Additives

Release agent

Applications

Automotive