



Makrolon® AX2475 MAS098

PC

Covestro Deutschland AG

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	19	cm³/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2400	MPa	ISO 527
Yield stress	65	MPa	ISO 527
Yield strain	6	%	ISO 527
Nominal strain at break	>50	%	ISO 527
Stress at Break	65	MPa	ISO 527
Strain at Break	>50	%	ISO 527
Impact Strength (Charpy), +23°C	no break	kJ/m²	ISO 179/1eU
Flexural Modulus (23°C)	2200	MPa	ISO 178
Notched Impact Strength (Izod), 23°C	65	kJ/m²	ISO 180/1A

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (1.80 MPa)	124	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	137	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	145	°C	ISO 306
Coeff. of Linear Therm. Expansion, parallel	65	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	65	E-6/K	ISO 11359-1/-2

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Melt temperature	280	°C	-
Mold temperature	80	°C	-
Injection speed	200	mm/s	-

Characteristics

Processing

Injection Molding

Applications

Automotive

Additives

Release agent