



Makrolon® 8345

PC-GF35

Covestro Deutschland AG

- MVR (300 °C/1.2 kg) 3.0 cm³/10 min
- 35 % glass fiber reinforced
- high viscosity
- easy release

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	3	cm³/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	9400	MPa	ISO 527
Yield stress	113	MPa	ISO 527
Yield strain	1.9	%	ISO 527
Tensile Creep Modulus, 1h	9000	MPa	ISO 899-1
Tensile Creep Modulus, 1000h	8500	MPa	ISO 899-1
Impact Strength (Charpy), +23°C	40	kJ/m²	ISO 179/1eU
Impact Strength (Charpy), -30°C	45	kJ/m²	ISO 179/1eU
Puncture - maximum force, +23°C	900	N	ISO 6603-2
Puncture - maximum force, -30°C	900	N	ISO 6603-2
Puncture energy, +23°C	5	J	ISO 6603-2
Puncture energy, -30°C	5	J	ISO 6603-2

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (1.80 MPa)	140	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	144	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	148	°C	ISO 306
Coeff. of Linear Therm. Expansion, parallel	20	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	60	E-6/K	ISO 11359-1/-2
Burning Behav. at 1.5 mm Nom. Thickn.	V-1	class	UL 94
Thickness tested	1.5	mm	-
Burning Behav. at thickness h	V-0	class	UL 94
Thickness tested	3.0	mm	-
Oxygen index	35	%	ISO 4589-1/-2

Electrical Properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 100Hz	3.6	-	IEC 62631-2-1
Relative permittivity, 1MHz	3.6	-	IEC 62631-2-1
Dissipation Factor, 100Hz	10	E-4	IEC 62631-2-1
Dissipation Factor, 1MHz	90	E-4	IEC 62631-2-1
Volume Resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface Resistivity	>1E15	Ohm	IEC 62631-3-2
Electric Strength	36	kV/mm	IEC 60243-1
Comparative tracking index	175	-	IEC 60112

Other Properties	Value	Unit	Test Standard
ISO Data			
Water Absorption	0.2	%	Sim. to ISO 62
Humidity absorption	0.1	%	Sim. to ISO 62
Density	1480	kg/m³	ISO 1183

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	300	°C	ISO 294
Injection Molding, mold temperature	110	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294

Makrolon® 8345


PC-GF35

Covestro Deutschland AG

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	2 - 3	h	-
Processing humidity	≤0.02	%	-
Melt temperature	310 - 330	°C	-
Mold temperature	80 - 130	°C	-

Diagrams


Viscosity-shear rate




Shearstress-shear rate



Dynamic Shear modulus-temperature




Stress-strain




Makrolon® 8345
PC-GF35

Covestro Deutschland AG


Secant modulus-strain




Stress-strain (isochronous) 23 °C



Creep modulus-time 23 °C




Stress-strain (isochronous) 40 °C




Makrolon® 8345
PC-GF35

Covestro Deutschland AG


Creep modulus-time 40 °C




Stress-strain (isochronous) 60 °C



Creep modulus-time 60 °C



Stress-strain (isochronous) 90 °C




Makrolon® 8345


PC-GF35

Covestro Deutschland AG


Creep modulus-time 90 °C



Stress-strain (isochronous) 120 °C



Creep modulus-time 120 °C



Characteristics

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets

Additives

Release agent

Special Characteristics

Opaque

Injection Molding

PREPROCESSING

Max. Water content: 0.01 - 0.02 %

Drying temperature: 120 °C

Drying time:

Circulating air drying oven (50 % fresh air) 4-8 h

Fresh air dryer (high speed dryer) 2-4 h

Makrolon® 8345

PC-GF35

Covestro Deutschland AG

Dry air dryer 2-3 h

PROCESSING

Melt temperature: 310-330 °C

Mold temperature: 80-130 °C

Use open nozzle.
