



Makrolon® M830 GF
PC-GF30

Covestro Deutschland AG

- polycarbonate
- MVR (300 °C/1.2 kg) 3.0 cm³/10 min
- high viscosity
- 30 % Glass fiber reinforced
- biocompatible according to many ISO 10993-1 test requirements
- suitable for medical devices

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	3	cm³/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	7800	MPa	ISO 527

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (1.80 MPa)	142	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	147	°C	ISO 75-1/-2
Coeff. of Linear Therm. Expansion, parallel	20	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	40	E-6/K	ISO 11359-1/-2

Other Properties	Value	Unit	Test Standard
ISO Data			
Water Absorption	0.26	%	Sim. to ISO 62
Humidity absorption	0.1	%	Sim. to ISO 62
Density	1420	kg/m³	ISO 1183

Characteristics

Certifications

Biocompatibility ISO 10993

Applications

Medical