



Makrolon® M410 GF

PC-GF10

Covestro Deutschland AG

- polycarbonate
- MVR (300 °C/1.2 kg) 12 cm³/10 min
- low viscosity
- 10 % glass fiber reinforced
- biocompatible according to many ISO 10993-1 test requirements
- suitable for medical devices

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	12	cm³/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5	%	ISO 294-4, 2577

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3800	MPa	ISO 527

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (1.80 MPa)	135	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	142	°C	ISO 75-1/-2
Coeff. of Linear Therm. Expansion, parallel	40	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	40	E-6/K	ISO 11359-1/-2

Other Properties	Value	Unit	Test Standard
ISO Data			
Water Absorption	0.3	%	Sim. to ISO 62
Humidity absorption	0.12	%	Sim. to ISO 62
Density	1270	kg/m³	ISO 1183

Characteristics

Certifications

Biocompatibility ISO 10993

Applications

Medical