

SKYGREEN® MP200

PETG

SK Chemicals

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0035	mm/mm	ASTM D 955
Density, 73 °F	1270	kg/m³	ASTM D 792

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Yield stress	49	MPa	ISO 527
Yield strain	4.1	%	ISO 527
Stress at Break	23	MPa	ISO 527
Strain at Break	40	%	ISO 527
Flexural Modulus (23 °C)	1890	MPa	ISO 178
Flexural strength	67	MPa	ISO 178
Notched Impact Strength (Izod), 23 °C	7	kJ/m²	ISO 180/1A
ASTM Data			
Tensile Strength at Yield	46.1	MPa	ASTM D 638
Tensile Strength at Break	46.1	MPa	ASTM D 638
Elongation at Yield	4.5	%	ASTM D 638
Elongation at Break	120	%	ASTM D 638
Flexural Modulus	1893	MPa	ASTM D 790
Flexural Strength	70.6	MPa	ASTM D 790
Rockwell Hardness	R 105	-	ASTM D 785
Notched Impact Strength (Izod), 1/8 in	105	J/m	ASTM D 256

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (1.80 MPa)	62	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	72	°C	ISO 75-1/-2
ASTM Data			
DTUL @ 66 psi	70	°C	ASTM D 648
DTUL @ 264 psi	62	°C	ASTM D 648

Optical Properties	Value	Unit	Test Standard
ASTM Data			
Haze	1	%	ASTM D 1003
Light Transmittance	90	%	ASTM D 1003

Characteristics

Processing

Injection Molding

Chemical Resistance

General Chemical Resistance

Special Characteristics

Transparent

Applications

Medical