

Adstif HA622M

PP HOMO

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	7	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Yield stress	40	MPa	ISO 527
Stress at Break	28	MPa	ISO 527
Flexural Modulus (23°C)	2200	MPa	ISO 178

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (0.45 MPa)	130	°C	ISO 75-1/-2

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	900	kg/m³	ISO 1183

Characteristics

Processing	Certifications
Film Extrusion	Food approval

Special Characteristics	Applications
Heat aging stabilized	Packaging

Features
Barrier Properties, High Crystallinity, Nucleated, Homopolymer