

Adstif HA1152

PP HOMO

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	25	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2000	MPa	ISO 527
Yield stress	40	MPa	ISO 527
Yield strain	6	%	ISO 527
Strain at Break	15	%	ISO 527
Impact Strength (Charpy), +23°C	60	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	2	kJ/m ²	ISO 179/1eA
Ball Indentation Hardness	93	MPa	ISO 2039-1

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (0.45 MPa)	110	°C	ISO 75-1/-2
Vicat softening temperature A	158	°C	ISO 306
Vicat softening temperature, 50°C/h 50N	104	°C	ISO 306

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	900	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Applications

Packaging

Features

High Crystallinity, Homopolymer