

Adsyl 7641 XCP

PP OTHERS

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	5.5	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	132	°C	ISO 11357-1/-3
Temp. of deflection under load (0.45 MPa)	62	°C	ISO 75-1/-2
Vicat softening temperature A	107	°C	ISO 306

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	900	kg/m³	ISO 1183

Optical Properties	Value	Unit	Test Standard
ASTM Data			
Gloss	87	-	ASTM D 2457
Haze	1	%	ASTM D 1003

Characteristics

Processing

Film Extrusion, Other Extrusion

Additives

Antiblocking agent

Features

Heat Sealable

Certifications

Food approval

Applications

Packaging