

CirculenRecover PP300T Grey

PP COPO

LyondellBasell Industries

CirculenRecover PP300T Grey contains at least 98% of recycled material.

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	50	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1200	MPa	ISO 527
Tensile Strength	26	MPa	ISO 527
Strain at Break	20	%	ISO 527
Notched Impact Strength (Charpy), +23°C	4.5	kJ/m ²	ISO 179/1eA

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	915	kg/m ³	ISO 1183
Bulk density	560	kg/m ³	-

Characteristics

Processing

Injection Molding

Certifications

Recycled Resin Content

Delivery form

Pellets

Applications

General Purpose, Packaging

Features

Copolymer, Impact Copolymer